

Property	6mil	12mil	Test Method
Tensile Strength (psi)			ASTM D-882
<i>Machine</i>	3597	3680	
<i>Transverse</i>	3373	3070	
Graves Tear (lbs/in.)			ASTM D-1004
<i>Machine</i>	441	429	
<i>Transverse</i>	447	436	
Internal Tear Resistance (g/mil)			ASTM D-689
<i>Machine</i>	262	257	
<i>Transverse</i>	266	337	
Water Extraction (%)	0.13	0.21	ASTM D-1239
Volatility (%)	2.71	0.85	ASTM D-1203
Cold Impact @ 0- -2⁰ F.	PASS	PASS	ASTM D-1593

6/12 mil PVC

